PAGE 5/10 * RCVD AT 11/19/2003 6:53:23 PM [Eastern Standard Time] * SVR:USPTO-EFXRF-2/0 * DNIS:7468000 * CSID:9494501764 * DURATION (mm-ss):02-18

Appl. No. 10/027,136 Amdt. Dated November 19, 2003 Reply to Office Action of August 19, 2003 Docket No. ONDAT-019US

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 1. (currently amended) A gas-generating composition comprising consisting essentially of:
 - (a) ammonium nitrate;
 - (b) metal oxyacid salt which produces a basic substance in combustion;
 - (c) ammonium perchlorate; and
- (d) at least one kind of combusting component selected from the group consisting of polymer binder, energetic material, and microcrystalline carbon powder, wherein the ammonium nitrate constitutes between 50 and 97 weight % of the sum of the ammonium nitrate, the metal oxyacid salt, and the ammonium perchlorate.
- 2. (original) A gas-generating composition according to Claim 1, wherein the metal oxyacid salt comprises at least one compound selected from the group consisting of alkali metal nitrate, alkali metal nitrate, alkali earth metal nitrate, and alkali earth metal nitrate.
- 3. (original) A gas-generating composition according to Claim 2, wherein the metal oxyacid salt is alkali metal nitrate, and the molar ratio of the ammonium perchlorate with respect to the alkali metal nitrate is between 0.8 and 1.2.
- 4. (withdrawn) A gas-generating composition according to Claim 2, wherein the metal oxyacid salt is alkali metal nitrite, and the molar ratio of the ammonium perchlorate with respect to the alkali metal nitrite is between 0.8 and 1.2.
- 5. (withdrawn) A gas-generating composition according to Claim 2, wherein the metal oxyacid salt is alkali earth metal nitrate, and the molar ratio of the ammonium perchlorate with respect to the alkali earth metal nitrate is between 1.6 and 2.4.
- 6. (original) A gas-generating composition according to Claim 2, wherein the metal oxyacid salt is

Page 2

PAGE 6/10 " RCVD AT 1/19/2003 6:53:23 PM [Eastern Standard Time] " SVR:USPTO-EFXRF-2/0 " DNIS:7468000 " CSID:9494501764" DURATION (mm-ss):02-18

Appl. No. 10/027,136 Amdt. Dated November 19, 2003 Reply to Office Action of August 19, 2003 Docket No. ONDAT-019US

alkali earth metal nitrite, and the molar ratio of the ammonium perchlorate with respect to the alkali earth metal nitrite is between 1.6 and 2.4.

7. (original) A gas-generating composition according to Claim 1, wherein the combusting component constitutes between 2 and 60 weight % of the sum of the ammonium nitrate, the metal oxyacid salt, the ammonium perchlorate, and the combusting component.

8. (original) A gas-generating composition according to Claim 1, wherein the metal oxyacid salt is potassium nitrate, and said ammonium nitrate is phase-stabilized ammonium nitrate, which is phase-stabilized by using said potassium nitrate.

9. (canceled)

- 10. (original) A gas-generating composition according to Claim 1, wherein the oxygen-balance value of the gas-generating composition is between -0.1 and +0.1 (g/g).
- 11. (original) A gas-generating composition for vehicle passenger protecting device, comprising:
- (a) phase-stabilized ammonium nitrate having an average particle size between 1 and $1000 \, \mu$ m;
 - (b) potassium nitrate having an average particle size between 1 and 1000 μ m;
 - (c) ammonium perchlorate having an average particle size between 1 and 1000 µ m; and
- (d) microcrystalline carbon powder having an average particle size between 1 and 500
 μ m,

wherein the phase-stabilized ammonium nitrate constitutes between 50 and 97 weight % of the sum of the phase-stabilized ammonium nitrate, the potassium nitrate, and the ammonium perchlorate.



PACE 7/10 * RCVD AT 11/19/2003 6:33:23 PM [Eastern Standard Time] * SVR. USPTO-EFXRF-2/0 * DMIS:7468000 * CSID:9494501764 * DURATION (mm-ss):02-18

Appl. No. 10/027,136 Amdt. Dated November 19, 2003 Reply to Office Action of August 19, 2003 Docket No. ONDAT-019US

- 12. (new) A gas-generating composition for vehicle passenger protecting device, comprising:
 - (a) phase-stabilized ammonium nitrate;
 - (b) potassium nitrate;
 - (c) ammonium perchlorate; and
 - (d) microcrystalline carbon powder,

wherein the phase-stabilized ammonium nitrate constitutes between 50 and 97 weight % of the sum of the phase-stabilized ammonium nitrate, the potassium nitrate, and the ammonium perchlorate.

- 13. (new) A gas-generating composition for vehicle passenger protecting device, comprising:
 - (a) phase-stabilized ammonium nitrate;
 - (b) nitrate of alkali metal or alkali earth metal;
 - (c) ammonium perchlorate; and
 - (d) microcrystalline carbon powder,

wherein the phase-stabilized ammonium nitrate constitutes between 50 and 97 weight % of the sum of the phase-stabilized ammonium nitrate, the nitrate, and the ammonium perchlorate.

- 14. (new) A gas-generating composition for vehicle passenger protecting device, comprising:
 - (a) phase-stabilized ammonium nitrate;
 - (b) nitrate of alkali metal or alkali earth metal;
 - (c) ammonium perchlorate; and
 - (d) microcrystalline carbon powder.
- 15. (new) A gas-generating composition consisting essentially of:
 - (a) ammonium nitrate;
 - (b) metal oxyacid salt which produces a basic substance in combustion;
 - (c) ammonium perchlorate;





PAGE 8110 * RCVD AT 1119/2003 6:53:23 PM [Eastern Standard Time] * SVR:USPTO-EFXRF-210 * DNIS:7468000 * CSID:9494501764 * DURATION (mm-ss):02-18

Appl. No. 10/027,136 Amdt. Dated November 19, 2003 Reply to Office Action of August 19, 2003 Docket No. ONDAT-019US

(d) at least one kind of combusting component selected from the group consisting of polymer binder, energetic material, and microcrystalline carbon powder, wherein the ammonium nitrate constitutes between 50 and 97 weight % of the sum of the ammonium nitrate, the metal oxyacid salt, and the ammonium perchlorate; and

(e) at least one of;

a stabilizer, and

a combustion catalyst.

